

forming the partitioning member above the substrate, the partitioning member having openings corresponding to pixel areas;

independently filling each of the openings with a composition for the hole injecting and transporting layer using an ink-jet recording head, the composition comprising (1) a conductive material containing at least a lubricant, polyethylene dioxythiophene and polystyrene sulfonic acid, and (2) a solvent; and

drying the composition filled in the openings to form the hole injecting and transporting layer.

56. (Three Times Amended) A manufacturing process for an organic EL element having a stacked structure including a hole injecting and transporting layer and a light-emitting layer formed within a partitioning member which is divided into individual pixel areas, the method comprising:

forming the partitioning member above the substrate, the partitioning member having openings corresponding to pixel areas;

independently filling each of the openings with a composition for the hole injecting and transporting layer using an ink-jet recording head, the composition comprising at least a material for the hole injecting and transporting layer, a lubricant, and a polar solvent; and

drying the composition filled in the openings to form the hole injecting and transporting layer.

62. (Three Times Amended) A method for manufacturing an electroluminescent display, the method comprising:

(1) manufacturing an EL element, wherein the step of manufacturing the EL element comprises:

forming a partitioning member above the substrate, the partitioning member having openings corresponding to pixel areas;

independently filling each of the openings with a composition for a hole injecting and transporting layer using an ink-jet recording head, the

composition comprising (a) a conductive material containing at least a lubricant, polyethylene dioxythiophene and polystyrene sulfonic acid, and (b) a solvent; and

drying the composition filled in the openings to form the hole injecting and transporting layer; and

(2) incorporating the manufactured EL element into the electroluminescent display.

63. (Three Times Amended) A method for manufacturing an electroluminescent display, the method comprising:

(1) manufacturing an EL element, wherein the step of manufacturing the EL element comprises:

forming a partitioning member above the substrate, the partitioning member having openings corresponding to pixel areas;

independently filling each of the openings with a composition for a hole injecting and transporting layer using an ink-jet recording head, the composition comprising at least a material for the hole injecting and transporting layer, a lubricant, and a polar solvent; and

drying the composition filled in the openings to form the hole injecting and transporting layer; and

(2) incorporating the manufactured EL element into the electroluminescent display.